



DATA SHEET (effective 03/25/08)

CKJN200 Typical OleTex Foam Properties

Standard Test	ASTM D 3575	CKJN200
Density (lb/cu ft)	Suffix W	2.0
Tensile Strength (psi)	Suffix T	42
Elongation (%)	Suffix T	115
Tear Resistance	Suffix G	11
Compressive Strength (psi)	Suffix D	
10% Deflection		2.6
25% Deflection		5.5
40% Deflection		9.6
50% Deflection		14
Compression Set (%)	Suffix B	25
Thermal Stability (% change) (24 Hours @ 158°F)	Suffix S	2
Water Absorption Lb/sq ft (skived)	Suffix L	< 0.07
Flammability	FMVSS302	¼" and thicker
Working Temperature Range		-65° to 210°F

Properties are averages of machine and cross direction

Series includes: CKJN/CKJV/CKJW

For updates to this document please refer to our website.

Armacell provides this information as a technical service. To the extent the information is derived from sources other than Armacell, Armacell is substantially, if not wholly, relying upon the other source(s) to provide accurate information. Information provided as a result of Armacell's own technical analysis and testing is accurate to the extent of our knowledge and ability, using effective standardized methods and procedures. Each user of these products, or information, should perform their own tests to determine the safety, fitness and suitability of the products, or combination of products, for any foreseeable purposes, applications and uses by the user and by any third party to which the user may convey the products. Since Armacell cannot control the end use of this product, Armacell does not guarantee that the user will obtain the same results as published in this document. The data and information is provided as a technical service, and the data and information are subject to change without notice.

Armacell LLC • 16800 South Canal Street • South Holland, IL 60473
 email: info.us@armacell.com • www.armacell.com

South Holland, IL • 800-343-1255 or 919 304-3846, ext. 8517 • fax: 708-596-9270

© 2008 Armacell LLC

CKJN200	01	03	08	NA	NA
---------	----	----	----	----	----

ALL ARMACELL FACILITIES IN NORTH AMERICA ARE
 ISO 9001:2000 OR ISO/TS 16949:2002 CERTIFIED

OleTex® is a registered trademark of Armacell